



2100. Kudjeljno uže DIN EN 1261-B



4-struka, sukano, izrađeno od prvoklasne kudjelje. Dostupno u namotima od 220 m (722 stopa) ili na drvenim bubnjevima.



Uže $\varnothing$ u mm	Težina u kg/100 m	Minimalna sila kidanja u daN	Kat. br.
8	4,7	450	2100.00.08
10	7,4	700	2100.00.10
12	11,1	1080	2100.00.12
16	18,5	1825	2100.00.16
20	28,5	2780	2100.00.20
24	41,0	3980	2100.00.24
30	64,0	6180	2100.00.30
36	93,0	8560	2100.00.36

2200. Poliamidno uže DIN EN 696-A

3-struka, sukano, termo-stabilizirano, siva boja. Dostupno u namotima od 220 m (722 stopa) ili na bubnjevima.



Uže $\varnothing$ u mm	Težina u kg/100 m	Minimalna sila kidanja u daN	Kat. br.
8	4	1320	2200.00.08
10	6,2	2040	2200.00.10
12	8,9	2940	2200.00.12
16	15,8	5200	2200.00.16
20	24,5	8140	2200.00.20
24	35,5	11800	2200.00.24
30	55,5	17400	2200.00.30
36	80	24400	2200.00.36

2310. Polipropilensko uže grade 1 DIN 83329-A

3-struka, izrađeno od modificiranog pletiva za uže upotrebom posebne metode. Dostupno u namotima od 220 m (722 stopa) ili na drvenim bubnjevima.



Uže $\varnothing$ u mm	Težina u kg/100 m	Minimalna sila kidanja u daN	Kat. br.
8	2,8	595	2310.00.08
10	4,3	900	2310.00.10
12	6,3	1340	2310.00.12
16	10,4	2180	2310.00.16
20	16,0	3420	2310.00.20
24	23,0	4830	2310.00.24
30	35,0	7300	2310.00.30
36	51,0	10400	2310.00.36

2210. Poliamidna pletenica DIN 83307-E

8-strukova, pleteno, siva boja. Dostupno u dužini od 100 m (328 stopa) na drvenom bubnju (križu).



Uže $\varnothing$ u mm	Težina u kg/100 m	Minimalna sila kidanja u daN	Kat. br.
1	0,07	30	2210.00.10
1,5	0,13	40	2210.00.15
2	0,18	100	2210.00.20
2,5	0,28	140	2210.00.25
3	0,51	180	2210.00.30
4	0,90	270	2210.00.40
6	2,00	610	2210.00.60
8	3,60	1000	2210.00.80
10	5,60	2400	2210.01.00

